

品 種			取扱粒度	孔径寸法 残留率	保証値			目 標 値					塩酸可溶鉄 (Fe <sub>2</sub> O <sub>3</sub> %)
MM	MMS	SM											
○			8~5mm	micron %	+8000 10max.	-4750 10max.	8000/6700 10~25	6700/5600 25~45	5600/4750 30~50				0.010 max.
○			7~3mm	micron %	+6700 10max.	-2800 5max.	6700/4750 30~50	4750/3350 40~60	3350/2800 5~15				0.010 max.
○			5~3mm	micron %	+4750 15max.	-2800 5max.	4750/4000 25~45	4000/3350 35~55	3350/2800 10~25				0.010 max.
○			5~2mm	micron %	+4750 10max.	-1700 5max.	4750/4000 10~25	4000/2800 35~55	2800/1700 25~45				0.010 max.
○			-5mm	micron %	+4750 5max.	-1000 30max.	4750/3350 15~30	3350/2360 15~30	2360/1700 10~20	1700/1000 10~20			0.020max.
○			5~10mesh	micron %	+4000 5max.	-1700 5max.	4000/3350 20~35	3350/2360 45~65	2360/1700 10~25				0.010max.
○			3.5~1mm	micron %	+3350 20max.	-1000 5max.	3350/2360 30~50	2360/1700 15~30	1700/1000 15~30				0.010 max.
○			-3mm	micron %	+2800 5max.	-500 30max.	2800/2360 15~25	2360/1700 15~30	1700/1000 20~40	1000/500 10~25			0.020max.
○		○	2.83~1mm	micron %	+2800 5max.	-1000 5max.	2800/1700 45~65	1700/1000 30~50					0.010max.
○			8~32mesh	micron %	+2360 5max.	-500 5max.	2360/2000 10~25	2000/1700 10~25	1700/1000 30~50	1000/500 10~25			0.010max.
○			2~1mm	micron %	+2000 5max.	-1000 10max.	2000/1400 35~60	1400/1000 30~55					0.010max.
○			10~20mesh	micron %	+1700 10max.	-850 5max.	1700/1180 50~75	1180/850 20~40					0.020 max.
○			1~0.5mm	micron %	+1000 10max.	-500 10max.	1000/850 20~40	850/710 20~40	710/500 25~45				0.020 max.
○			1~0.3mm	micron %	+1000 5max.	-300 5max.	1000/710 20~40	710/500 20~35	500/300 25~45				0.020max.
○			35~100mesh	micron %	+500 2max.	500/425 5~20%	-150 3max.	425/300 35~55	300/180 35~55				0.020 max.
○			-8mesh	micron %	+2360 10max.	-425 15max.	2360/1700 25~35	1700/1180 15~25	1180/425 25~35				0.020 max.
○		○	-1mm	micron %	+1000 5max.	-250 40max.	1000/500 40~60	500/250 20~40					0.050 max.
○			-0.5mm	micron %	+500 10max.	-150 45max.	500/250 30~50	250/150 10~25					0.050 max.
○			-740 μ m	micron %	+710 2max.	-45 45max.	710/500 10max.	500/300 5~15	300/150 10~25	150/75 15~30	75/45 10~25		0.300 max.
○	○		-100mesh	micron %	+150 10max.	-45 60max.	150/75 20~40	75/45 15~30					0.300 max.
○			-150mesh	micron %	150/106 10max.	-45 80max.	106/75 5~15	75/45 10~25					0.300max.
○			-200mesh(A)	micron %	+150 0	-45 75~85	150/75 10max.	75/45 10~25					0.100 max.
○			-200mesh	micron %		+150 3max.	150/75 5max.						0.300 max.
○	○	○	-325mesh	micron %		+45 5max.	-20 55~75						0.300max.

※ ○印が通常取扱い商品となります。